

## Reveal Edge B

### PRODUCT DESCRIPTION

Reveal Edge is a range of bonded metallic powder coatings, developed with the designer in mind, to provide outstanding colours and finishes. The product has great recyclability and options for high corrosion resistance.

#### Application areas

This product is recommended for interior use on surfaces exposed to a dry environment.

Typical application areas:

Home furniture

Office furniture

Shop fittings and lighting, sports equipment

### POWDER PROPERTIES

Property	Standard	Result
Specific gravity	ISO 8130	Typically $1.4 \pm 0.2 \text{ g/cm}^3$

#### Storage

Keep in a dry cool area. Maximum temperature 25 °C. Maximum relative humidity 60 %. If stored longer than 12 months a quality test must be performed.

### APPLICATION

#### Pretreatment

The overall performance of the coating system is largely dependent on the nature of the substrate and the type and quality of the pretreatment. For optimal results, it is recommended to follow the pretreatment supplier's instructions and recommendations.

#### Powder application

Curing schedule	Object temperature	Time
Reveal Edge B0	200 °C	10 minutes
Reveal Edge B8	180 °C	10 minutes
Reveal Edge B6	160 °C	10 minutes

Recommended minimum film thickness 60 µm.

Some sparkling products may require a higher thickness for full hiding depending on substrate.

#### Equipment

Suitable for Corona charging equipment.

### APPEARANCE

<b>Colour</b>	Available in a wide variety of metallic colours and effects upon technical approval.
<b>Gloss</b>	Gloss levels are dependent on the effect and finish required.
<b>Finish</b>	Smooth and textured finishes
Metallic/special effect powder coatings are more sensitive to variations in application, it is important to consider recommendations given in our Application Guidelines for Metallic Powder Coatings.	

## PERFORMANCE

The technical data provided below are typical for this product when applied as follows:

Substrate	Iron-phosphated cold rolled steel
Substrate thickness (mm)	0.8
Film thickness (µm)	60-80
Typical values when tested.	

Property	Standard	Result
<b>Adhesion</b>	ISO 2409	Cross-cut rating Gt0 (100 % adhesion)
<b>Cupping test</b>	ISO 1520	≥ 5 mm
<b>Impact resistance</b>	ASTM D2794 (5/8 " ball) (inch-pounds, front and reverse) Smooth, gloss > 60 Smooth, gloss 20-39 Smooth, gloss < 40 Fine texture Coarse texture	100/80 60/40 40/20 40/20 40/20
<b>Resistance to neutral salt spray</b>	ISO 9227	No blistering and maximum 1 mm corrosion creep from scribe after 240 hours
<b>Resistance to humid atmospheres</b>	ISO 6270-2	No blistering and maximum 2 mm corrosion creep from scratch after 500 hours

## Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.